



ARDEX F 200

Internal Wall Smoothing Compound (BASE)

Advantages

- High Bond Strength
- Easy to Trowel
- Crack-Resistant
- Eco-Friendly & Non-Toxic



Description

ARDEX F 200 is formulated with selected fillers and pigments and blended with multiple high-quality additives. It develops high bond strength to the substrate and is easy to trowel.

Areas of Application

Suitable for skim coating and levelling interior walls and ceilings.
Suitable for thick application.

Substrate Preparation

The substrate must be sound and flat. Remove any remaining loose materials and contaminants; fill and repair holes and cracks. The substrate must have adequate load-bearing capacity.

Mixing

Pour clean water into a clean container, then add ARDEX F 200 powder and immediately mix until a uniform, lump-free consistency is achieved. Mechanical mixing is recommended. The mixing ratio by weight is: 20 kg ARDEX F 200 powder with approx. 8 L clean water. Adjust the water addition as appropriate according to actual conditions.

The above water dosage is based on tests carried out by our company at room temperature using standard mixing equipment; different mixers may affect the required water amount.

ARDEX F 200

Internal Wall Smoothing Compound (BASE)

Application

After mixing, use appropriate tools to trowel the paste onto the substrate, and use up the material before initial set. The recommended application thickness is 2 mm–20 mm; for thicknesses over 20 mm, apply in multiple coats. The application temperature must not be lower than 5°C.

Packaging

20 kg per bag

Standard

GB/T 28627-2023

Storage & Shelf Life

Shelf life 12 months when unopened and stored in a cool, dry place.

Health & Safety

Wear work clothing, gloves, and protective goggles during use. After work, wash contacted areas with clean water and soap. If the product accidentally splashes into the eyes, rinse immediately with plenty of clean water and seek medical attention. Keep out of reach of pregnant women and children. Ensure adequate ventilation during use.